



1-800-280-0712 • (541)447-0712 • FAX (541)447-0759  
3451 SW Empire Dr • Prineville, OR 97754  
[info@btlliners.com](mailto:info@btlliners.com) • [www.btlliners.com](http://www.btlliners.com)

**Strength-Commitment-Guaranteed Containment**

## **PPL-36 CONTAINMENT MEMBRANE**

**LOW TEMPERATURE - HYDROCARBON STABLE**

<b>DESCRIPTION</b>	BLACK TAPE, Dual 14x14(1500d) COUNT PER INCH	
<b>FABRICATION &amp; WAREHOUSE</b>	PRINEVILLE, OREGON	
<b>WEIGHT</b>	19.1 OZ./SQ.YD. (+/-10%)	ASTM D 1910
<b>THICKNESS</b>	36 MILS (+/-10%)	
<b>COATING THICKNESS</b>	2.0 MILS & 2.25 MILS (+/-10%)	
<b>TENSILE STRENGTH</b> (GRAB METHOD)	WARP 666 LBS. WEFT 519 LBS.	ASTM D 751
<b>ELONGATION TO BREAK</b>	WARP 28% WEFT 21%	
<b>TEAR STRENGTH</b> (TONGUE METHOD)	WARP 108 LBS/INCH WEFT 134 LBS/INCH	ASTM D 751
<b>BURSTING STRENGTH</b> (MULLEN)	993 PSI	ASTM D 3786
<b>BURSTING STRENGTH</b> (BALL)	803 PSI	ASTM D 3776
<b>HYDROSTATIC RESISTANCE</b>	360 PSI	ASTM D 751A
<b>MOISTURE VAPOR TRANSMISSION</b>	0.7076 GRAMS/M2/24HRS.	ASTM E 96 B
<b>LOW TEMPERATURE COLD CRACK</b>	-65F	ASTM D 2136

ALL DATA IS DRAWN FROM U.S. TESTING, PRECISION LABORATORIES AND TRI  
ENVIROMENTAL AND ARE AVAILABLE ON REQUEST.