



BTL™-10

Clear Greenhouse Material

LOW TEMPERATURE - HYDROCARBON STABLE

Coated on both sides with high UV stabilized LDPE coating

FABRICATION & WAREHOUSE	PRINEVILLE, OREGON	
WEIGHT	5.8 OZ./SQ.YD. (+/-10%)	
THICKNESS	10 MILS (+/-10%)	
COATING THICKNESS	2.1 MILS EACH (+/-10%)	
TENSILE STRENGTH (GRAB METHOD)	WARP 207 LBS. WEFT 157 LBS.	ASTM D 751
TEAR STRENGTH (TONGUE METHOD)	WARP 62 LBS/INCH WEFT 67 LBS/INCH	ASTM D 2261
LIGHT TRANSMITTANCE	Visible 85%	ASTM D 1003

ALL DATA IS DRAWN FROM U.S. TESTING AND PRECISION LABORATORIES. AVAILABLE ON REQUEST.