



## BTL™-9 AC

Clear Greenhouse Material w/ Anti Condensate  
LOW TEMPERATURE - HYDROCARBON STABLE  
Coated on both sides with high UV stabilized LDPE coating

<b>FABRICATION &amp; WAREHOUSE</b>	PRINEVILLE, OREGON	
<b>WEIGHT</b>	5.3 OZ./SQ.YD. (+/-10%)	
<b>THICKNESS</b>	9 MILS (+/-10%)	
<b>COATING THICKNESS</b>	2.25 MILS EACH (+/-10%)	
<b>TENSILE STRENGTH</b> (GRAB METHOD)	WARP 150 LBS. WEFT 130 LBS.	ASTM D 5034
<b>TEAR STRENGTH</b> (TONGUE METHOD)	WARP 50 LBS/INCH WEFT 50 LBS/INCH	ASTM D 5884
<b>BURSTING STRENGTH</b> (MULLEN)	250 PSI	ASTM D 3786
<b>UV RESISTANCE</b>	>80% STRENGTH RETAINED AFTER 2000 HRS.	ASTM G-151
<b>LIGHT TRANSMITTANCE</b>	NIR 78% Visible 87% Diffusion/Haze 63%	ASTM D 1003

ALL DATA IS DRAWN FROM U.S. TESTING AND PRECISION LABORATORIES. AVAILABLE ON REQUEST.  
2018